



Galvalume Plus[‡]



Bright White



Smokey Pewter



Light Gray



Silver Metallic



Black



Matte Black



Dark Charcoal



Charcoal Gray




Deep Blue



Ivy Green



Colony Green



Mansard Brown



Burnished Slate



Aged Bronze



Medium Bronze



Dark Bronze



Coco Brown



Saddle Leather Brown



Rustic Red



Patriot Red



Orange*



Bright Copper



Tan



Desert Tan



Light Stone

[‡]Galvalume Plus has no uniformity of appearance guarantee. Each individual sheet, even upon delivery, may have a different color, gloss, sheen, texture or spangled appearance. If uniformity of appearance is required, a painted product is required.

COIL COLOR CHART

24 Gauge Color	Thermal Emittance ¹ Range 0 to 1	Solar Reflectance (TSR) ² Range 0 to 1	Film Integrity (Years)	Color Fade ASTM D 2244 (Years)	Chalk ASTM D 4214, Method A (Years)
Aged Bronze	0.86 ± 0.02	0.22	40	30	30
Black	0.86 ± 0.02	0.31	40	30	30
Bright Copper	0.89 ± 0.02	0.42	35	35	35
Bright White	0.85 ± 0.02	0.70	40	30	30
Burnished Slate	0.87 ± 0.02	0.32	40	30	30
Charcoal Gray	0.86 ± 0.02	0.36	40	30	30
Coco Brown	0.88 ± 0.02	0.34	40	30	30
Colony Green	0.89 ± 0.02	0.38	40	30	30
Dark Bronze	0.87 ± 0.02	0.24	40	30	30
Dark Charcoal	0.88 ± 0.02	0.21	40	30	30
Deep Blue	0.89 ± 0.02	0.27	40	30	30
Desert Tan	0.87 ± 0.02	0.42	40	30	30
Galvalume Plus	0.31 ± 0.02	0.68	n/a	n/a	n/a
Ivy Green	0.89 ± 0.02	0.31	40	30	30
Light Gray	0.87 ± 0.02	0.46	40	30	30
Light Stone	0.83 ± 0.02	0.59	40	30	30
Mansard Brown	0.87 ± 0.02	0.17	40	30	30
Matte Black	0.88 ± 0.02	0.26	40	30	30
Medium Bronze	0.87 ± 0.02	0.28	40	30	30
Orange ³	0.47 ± 0.02	0.52	n/a	n/a	n/a
Patriot Red	0.80 ± 0.02	0.42	40	30	30
Rustic Red	0.86 ± 0.02	0.39	40	30	30
Saddle Leather Brown	0.89 ± 0.02	0.30	40	30	30
Silver Metallic	0.83 ± 0.02	0.57	35	35	35
Smokey Pewter	0.88 ± 0.02	0.35	40	30	30
Tan	0.84 ± 0.02	0.50	40	30	30

¹ASTM C 1371 "Standard Test Method for Determination of Emittance of Materials Near Room Temperature Using Portable Emitters"

²ASTM C 1549 "Standard Test Method for Determination of Solar Reflectance Near Ambient Temperature Using a Portable Solar Reflectometer"

³No Warranty Available for Orange

Mueller, Inc. reserves the right to add or discontinue colors without notice.

MATERIAL PROVIDER



CALL: 877-2-MUELLER (877-268-3553)

CLICK: WWW.MUELLERINC.COM

COME BY: ONE OF OUR CONVENIENT LOCATIONS